

# Nukor

POLY / POLY CORE SPUN



- Excellent Strength Tenacity
- Excellent Colour Fastness
- High Resistance to Abrasion
- Excellent Seam Strength & Appearance
- Minimise Seam Puckering and Skipped Stitches
- Extensive Colour Range
- Chemical Resistance
- High Productivity





# Nukor

## Poly / Poly Core Spun 滌綸包芯線

A high performance sewing thread made from high tenacity low elongation stabilised polyester filament and staple fibre. Specially formulated lubrication coupled with the high tenacity of the polyester core construction makes it the perfect choice for sewing operations where fineness and strong seam strength are needed.

金泰線之滌綸包芯線，表現出色，採用高強力，低伸延度，定型滌綸纖維及長絲製造而成。韌力特強，加以專研之潤滑線油，用於精緻車縫、及縫口強力度要求之操作上，實乃完美之組合。

### FEATURES 特點

Excellent Strength Tenacity  
絕佳的相對強度

Excellent Colour Fastness  
色牢度高

High Resistance to Abrasion  
耐磨性高

Excellent Seam Strength & Appearance  
強力縫口，外表美觀

Minimise Seam Puckering  
縫口平滑

Minimise Skipped Stitches  
避免跳針

Extensive Colour Range  
顏色選擇廣泛

Chemical Resistance  
抗化性強

High Productivity  
生產效率高

### APPLICATION 功能

Blouse  
女恤衫

Jeans  
牛仔褲

Ski-wear  
雪褸

Underwear  
內衣

Jackets  
外套

Shirts  
男恤衫

Trousers  
西褲

### CATEGORY & TECHNICAL SPECIFICATION 類別及技術資料

Tex No.	Ticket No. 編號	Length/Cone 每個長度	Average Count Size 平均粗度 (dTex)	Average Strength 平均強度 (cN)	Average Elongation 平均伸延度 @Break (%)	Boiling Water Shrinkage 沸水收縮率 (%)	Dry Heat Shrinkage 乾熱收縮率 @150°C (%)
TEX 16	Tkt 220	5,000M	180	720	14.0	<1.0	<0.7
TEX 18	Tkt 180	5,000M	200	820	14.0	<1.0	<0.7
TEX 21	Tkt 150	5,000M	235	950	14.0	<1.0	<0.7
TEX 24	Tkt 120	5,000M	290	1,200	20.0	<1.0	<0.7
TEX 30	Tkt 100	5,000M	350	1,550	20.0	<1.0	<0.7
TEX 40	Tkt 75	4,000M	460	2,000	20.0	<1.0	<0.7
TEX 60	Tkt 50	3,500M	745	3,400	20.0	<1.0	<0.7
TEX 80	Tkt 36	3,000M	870	4,100	20.0	<1.0	<0.7
TEX 105	Tkt 28	3,000M	1,200	5,600	20.0	<1.0	<0.7
TEX 120	Tkt 25	3,000M	1,330	6,300	21.0	<1.0	<0.7
TEX 150	Tkt 22	2,000M	1,800	8,200	21.0	<1.0	<0.7
TEX 180	Tkt 18	1,000M	2,000	8,900	21.0	<1.0	<0.7
TEX 240	Tkt 12	1,000M	2,500	11,500	21.0	<1.0	<0.7

### WASHING COLOUR FASTNESS 洗水色牢度

ISO Designation

國際標準

ISO 105 - C06  
(Section B2S)

Soap Solution

皂溶液

4g/l Detergent +  
1 g/l Sodium Perborate

Temp

溫度

50°C  
+ / - 2°C

Time

時間

30 Min

Colour Change / Staining

沾色程度

Grade 4

